

key advantages to you, our customer



0.025mm to 21mm (.001" to .827")



Order 3m to 3t (10 ft to 6000 Lbs)



Delivery: within 3 weeks



Wire to your spec



E.M.S available



Technical support

SUPER DUPLEX available in:-

- Round wire
- Bars or lengths
- Flat wire
- Shaped wire
- Rope/Strand

Packaging

- Coils
- Spools
- Bars or lengths





Chemical Composition		Specifications	Key Features	Typical Applications	
Element	Min %	Max %	ISO 15156-3	Excellent resistance to stress corrosion	Oil and gas exploration
С	-	0.03	(NACE MR 0175)	cracking in chloride-bearing environments Excellent resistance to pitting and crevice corrosion	Marine application
Mn	-	1.2	Designations		
Si	-	0.80	W.Nr. 1.4410	High resistance to general corrosion	
S	-	0.015	UNS S32750 2507		
Р	-	0.035	AWS 169		
Cr	24.00	26.0			
Ni	6.0	8.0			
Мо	3.0	4.5			
N	0.24	0.35			
Cu	-	0.5			
Fe	В	٩L			

Density	7.8 g/cm ³	0.28 lb/in ³	
Melting Point	1350 °C 2460 °F		
Coefficient of Expansion	13.5 μm/m °C (25 – 100 °C)	7.5 x 10 ⁻⁶ in/in °F (70 – 200 °F)	
Modulus of Rigidity	77 kN/mm²	11000 ksi	
Modulus of Elasticity	200 kN/mm²	29000 ksi	

Heat Treatment of Finished Parts					
Condition as supplied by Alloy Wire	Туре	Temperature		Time (Hr)	Cooling
Condition as supplied by Alloy Wire		°C	°F	Time (nr)	Cooling
Annealed or Spring Temper	Stress Relieve	250	480	1	Air

Properties						
Can distan	Approx. tensile strength		Approx. operating temperature			
Condition	N/mm²	ksi	°C	°F		
Solution Annealed	700 – 900	102 – 131	-200 to +300	-330 to +570		
Spring Temper	1300 – 1900	189 – 276	-200 to +300	-330 to +570		

 $\label{thm:continuous} The above tensile strength \ ranges \ are \ typical. \ If you \ require \ different \ please \ ask.$





